



TECHNICAL DATA SHEET

DA660



DESCRIPTION

DA660 Accelerator is designed to improve the overall air dry and curing time of DIMENSION™ Single-Stage Enamels and Urethane Clearcoats, when these products are sprayed in cool temperatures. Do not use in baking situations as it may cause die back in metallic and mica colors.



MIXING

DA660 can be added to the following products **at 1-2 capfuls per ready-to-spray quart:**

- 1st DIMENSION™ National Rule Compliant Alkyd Enamel
- 1st DIMENSION™ Low VOC Alkyd Urethane
- 2nd DIMENSION™ National Rule Compliant Acrylic Enamel
- 2nd DIMENSION™ Low VOC Acrylic Urethane Enamel
- 3rd DIMENSION™ National Rule Compliant Urethane Enamel
- 3rd DIMENSION™ Low VOC H.S. Urethane Enamel

DIMENSION™ National Rule Compliant High Solids Urethane Clearcoat DC5000
DIMENSION™ 3.5 VOC High Solids Urethane Clearcoat DC3500

NOTE:

Do not use DA660 in these products when spraying in warm temperatures, or when baking. Doing so may cause severe die-back and loss of gloss of the coating.