

Distributed in

The United States of America: Peter Kwasny Inc. 62-64 Enter Lane, Islandia, NY 11749 Canada by Peter Kwasny Spraypaint Canada Inc. 2275 Lakeshore Blvd. West, Suite 530 Toronto, ON. M8V 3Y3

Toll free North America Phone: 1-844-426-6330 / Fax: 1-866-226-6434 order@kwasny.us / service@kwasny.us www.spraymax.com

SprayMax® 1K Plastic Adhesion Promoter 297 g NET WT. 10.5 oz Art. Nr. 3680009



Product

Description / Purpose	Ideal adhesion promoter for subsequent coatings on
	most plastics
Properties	 One light, thin, and even uniform spray
	 Excellent adhesion properties
	Dries very quickly
	Maximum flexibility
	Maximum yield
	 Colourless, with silver pigments
	 Can be topcoated with any conventional fillers
	and topcoats, e.g. SprayMax® 1K Acrylic Filler,
	2K Primer Filler, Plastic Colours, basecoats,
	2K topcoats.
Material base	Chlorinated polyolefines
Colour	Light silver colour shade
Solid content	5 % per weight
EPA Coating Category	Polyolefin Adhesion Promoters
	PAP Limit 2.5



CARB Aerosol Rule Coating Category (01/2017)

Substrate

Polyolefin Adhesion Promoters PAP Limit 2.5

PP, PP/EPDM, ABS, SAN, PC, PA, PUR-RIM, R-TPU, PPO, PBT, PUR-flexible foam, UP-GF plastics (cleaned and sanded).

The damaged area must be dry and free of grease and dust and all rust needs to be removed. Surface must be free from parting agent. It is recommended to temper surface.

Processing

Protection measures		Wear personal protection equipment. (respiratory mask/gloves/goggles) For more information, see safety data sheet.
Shake		Shake can thoroughly for at least 2 minutes from when the mixing balls are heard.
Spray to test		After shaking the can, test spray and check
		compatibility with the surface and the colour.
Spraying distance		6 - 8 inches / 15 - 20 cm
Spray passes		Dry film thickness 0.04 - 0.08 mil (1 - 2 μm)
		(1 light spray coat)
Processing conditions	ļ	Optimum application at 64° F - 77° F (18° C - 25° C) and a relative humidity from 40 - 50 %.



Coverage

Drying

Finish

Additional Information

Shelf Life

Disposal

approx. 64 - 86 sq ft (6 - 8 m²) / aerosol at approx. 0,08 mil (2 µm) dry film thickness

Can be topcoated with all conventional fillers and topcoats after 10 min airdrying.

After painting, turn the can upside down and spray the valve until empty.

60 months

The usage period refers to an unused can that is stored correctly at a temperature of 60° F - 77° F / 15 - 25° C and a relative humidity below 60%. The can must be stored and transported in an upright position in a dry place where it is protected against chemical and mechanical influences. The safety information on the can and all statutory provisions applicable for the storage site must be observed. The completely emptied spray cans must be disposed of in the recycling system. Cans with hardened material must be disposed of as special waste.

For professional use only. Identification, see safety data sheet.

The contents in this technical data sheet were created with great care and reflect our current state of knowledge. They provide the user with application-specific information and do not promise certain properties. The information is non-binding and we accept no liability for its integrity, accuracy and completeness. They do not relieve the user of their duty to check the suitability of our product for the intended purpose. The warnings printed on our labels must be respected. Our brands and patents are protected by copyright. All rights reserved. We reserve the right to update, amend or supplement the content of the information without prior notice.

Note